

## ALLSTONE POINTING MIXES 12/2013

### MIX 1

**New Desert Sand, Golden Sand,  
Sahara Cream**

6: White Sand	18 litres
1: Brown Sand	3 litres
1: White Cement	3 litres
2: Lime	6 litres
1: Uniflex Additive	1 litre

### MIX 2

**Sand Dune, Classic Adelaide,  
Drifting Sand**

6: Brown Sand	18 litres
1: White Cement	3 litres
1: Lime	3 litres
1: Uniflex Additive	1 litre

### MIX 3

**Dove Grey, Montana Blue**

6: White Sand	18 litres
1: Brown Sand	3 litres
1: Portland Cement	3 litres
2: Lime	6 litres
1: Uniflex Additive	1 litre

### MIX 4

**Old Adelaide, Ironbark**

6: Brown Sand	18 litres
1: Portland Cement	3 litres
1/3: Lime	1 litres
1: Uniflex Additive	1 litre

### MIX 5

**Cottage Blend**

5: White Sand	15 litres
2: Brown Sand	6 litres
1: White Cement	3 litres
2: Lime	6 litres
1: Uniflex Additive	1 litre

### MIX 6

**Amber Glow Crazy**

As for MIX 5 but reduce amount of  
Lime to 1

Each mix will cover approx. **6s.m.** for  
**flush/slightly recessed** pointing

Each mix will cover approx. **5s.m.** for  
**fine line** pointing

**Random Quartzite veneer** – each  
mix will cover approx. **4s.m.**

+ Add squirt of dishwashing liquid